




## 2x2 glazed hexagon mosaic




**GIGHX22WWBGL**  
standard white with black




**GIGHX22BLGL**  
black




**GIGHX22BISGL**  
biscuit



**GIGHX22TGGL**  
tender grey



**GIGHX22BNGL**  
bone



**GIGHX22TPGL**  
taupe



**GIGHX22WWGL**  
warm white


## 2x2 unglazed hexagon mosaic




**GIGHX22AWUN**  
arctic white




**GIGHX22BNUN**  
bone



**GIGHX22DGUN**  
dark grey




**GIGHX22BLUN**  
black



**GIGHX22SGUN**  
sterling grey

## 1x1 glazed hexagon mosaic



**GIGHX11WWBGL**  
standard white with black



**GIGHX11WTGL**  
standard white

### TECHNICAL SPECIFICATIONS

DESCRIPTION	RESULT	TEST METHOD (STANDARD)
Chemical Resistance	CLASS A	C650 Test
Water Absorption	0.05%	C373 Test
PEI	3	C1027 Test
C.O.F. (Wet) UNGLAZED	1.09	ASTM C1028
C.O.F. (Dry) UNGLAZED	0.77	ASTM C1028
C.O.F. (Wet) GLAZED	0.82	ASTM C1028
C.O.F. (Dry) GLAZED	0.61	ASTM C1028
Thickness	1/4" / 5.5mm	-
D.C.O.F.	N/A	BOT 3000